

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>50000	>50000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>454	>130	ISO1421:2016
Rupture Resistance	%	>224	>358	ISO1421:2016
Tear Strength	N	>52	>58	ISO4674-1 :2016
Peel Adhesion	N/5 cm	>64	>45	ISO 12947-2 :2016
Composition Textile	%	%24 Recycled Polyester +/- 2		
Bio PU	%	29% PVC	2 % Bio PU +/- 2	45 % Tea +/- 2
Weight	grmq	500 +/- 5%		
Thickness	mm	0,90 +/- 5		
Width	cm	145 +/- 5		

