

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>50000	>50000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>600	>530	ISO1421:2016
Rupture Resistance	%	>49	>104	ISO1421:2016
Tear Strength	N	>36	>27	ISO4674-1 :2016
Peel Adhesion	N/5 cm	>1,1	>1,4	ISO 12947-2 :2016
Composition	Textile	%	34,60 % Recycled Polyester +/- 2	
	Bio PU	%	30,60%Bio PU +/- 2 34,80 % Tea +/- 2	
Weight	grmq	500 +/- 5%		
Thickness	mm	0,95 +/- 5%		
Width	cm	140 +/- 5		



