

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>50000	>50000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>412	>307	ISO1421:2016
Rupture Resistance	%	>40	>119	ISO1421:2016
Tear Strength	N	>28	>27	ISO4674-1 :2016
Composition Textile Bio PU	15%	50%Organic Cotton+%50 Receycled Polyester +/- 2		
	%	64% PVC	3 % Bio PU +/- 2	18 % Tea +/- 2
Weight	grmq	800 +/- 5%		
Thickness	mm	1,10 +/- 5		
Width	cm	140 +/- 5		

