

| Data Sheet          | Units          | Longitudinally                        | Transverse | Test Method       |
|---------------------|----------------|---------------------------------------|------------|-------------------|
| Abrasion Resistance | Cycles (12Kpa) | >50000                                | >50000     | ISO 12947-2 :2016 |
| Tensile Strength    | N/5 cm         | >500                                  | >500       | ISO1421:2016      |
| Rupture Resistance  | %              | >47                                   | >113       | ISO1421:2016      |
| Tear Strength       | N              | >30                                   | >26        | ISO4674-1 :2016   |
| Peel Adhesion       | N/5 cm         | >1,3                                  | >1,7       | ISO 12947-2 :2016 |
| Composition Textile | %              | 34,60% Recycled Polyester +/- 2       |            |                   |
| Bio PU              | %              | 30,60 %Bio PU +/- 2 34,80 % Tea +/- 2 |            |                   |
| Weight              | grmq           | 500 +/- 5%                            |            |                   |
| Thickness           | mm             | 1,0 +/- 5%                            |            |                   |
| Width               | cm             | 140 +/- 5                             |            |                   |

