

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>50000	>50000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>427	>195	ISO1421:2016
Rupture Resistance	%	>52	>190	ISO1421:2016
Tear Strength	N	>15	>26	ISO4674-1 :2016
Peel Adhesion	N/5 cm	>20	>26	ISO 12947-2 :2016
Composition Textile	%	%34 Receycled Polyester +/- 2		
Bio PU	%	38% PVC	11 % Bio PU +/- 2	17 % Tea +/- 2
Weight	grmq	350 +/- 5%		
Thickness	mm	0,70 +/- 5		
Width	cm	145 +/- 5		

