

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>50000	>50000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>580	>550	ISO1421:2016
Rupture Resistance	%	>54	>122	ISO1421:2016
Tear Strength	N	>33	>25	ISO4674-1 :2016
Peel Adhesion	N/5 cm	>1,4	>1,6	ISO 12947-2 :2016
Composition Textile	%	34,60 % Recycled Polyester +/- 2		
Bio PU	%	30,60%Bio PU +/- 2 34,80 % Tea +/- 2		
Weight	grmq	500 +/- 5%		
Thickness	mm	1,2 +/- 5%		
Width	cm	140 +/- 5		

