

Data Sheet	Units	Longitudinally	Transverse	Test Method
Abrasion Resistance	Cycles (12Kpa)	>40000	>40000	ISO 12947-2 :2016
Tensile Strength	N/5 cm	>457	>238	ISO1421:2016
Rupture Resistance	%	>126	>381	ISO1421:2016
Tear Strength	N	>30	>53	ISO4674-1 :2016
Peel Adhesion	N/5 cm	>24	>20	ISO 12947-2 :2016
Composition Textile	%	%34 Recycled Polyester +/- 2		
Bio PU	%	38% PVC	11 % Bio PU +/- 2	17 % Tea +/- 2
Weight	grmq	350 +/- 5%		
Thickness	mm	0,70 +/- 5		
Width	cm	145 +/- 5		

